

## Adhesion Promoter

### GENERAL INFORMATION

Adherent ADP is an additive to improve adhesion of paint film especially on non-ferrous substrates. It is mainly used in stoving paints.

### PHYSICAL PROPERTIES

Composition	non-silicone polymeric compound
Appearance	clear liquid
Non-volatile content	78 - 82 %
Solvent	isopropanol
Specific gravity	1.08 - 1.10
Acid value	60 - 80 mg KOH / g

### APPLICATIONS

- Alkyd / melamine
- Acrylic / melamine

### KEY PROPERTIES

- To promote adhesion of stoving paints on difficult non-ferrous substrates such as aluminum, zinc, copper, brass, electroplated steel etc.
- To improve the flexibility and impact resistance of paint film.
- Thermo-stable that does not discolor at elevated temperature.
- No side-effect of shelf-life.

### INCORPORATION

The dosage depends on the adhesion property of resin as well as the substrate to be applied on.

Adherent ADP is incorporated during the any stage.

### LEVELS OF USE

1.5 - 2.5 % based on total formulation.

### HANDLING AND SAFETY

- Due to its acidic structure, loss of gloss may occur when Adherent ADP is combined with certain basic pigments. It is therefore recommended to check before practical application.
- Haze or separation may be found when Adherent ADP is stored under low temperature after a period of time. It can be recovered by carefully heating without influence on performance.
- As it contains solvents, the product requires special care in handling.
- Avoid any eye and skin contact.
- For further information please check to MSDS.

### STORAGE RECOMMENDATIONS

- Keep away from sources of ignition and heat.
- Keep container tightly closed a dry and well-ventilated place.
- Stored between 0°C to 40°C.
- Below 5°C appearance may be to cloud or solid-like, please heat(water bath) to clear then stir to uniform.
- Packing not to be exposed directly under heat radiation.

### PACKAGING

Net Weight: 200 kg / 25 kg

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*® Trademark of Elementis Specialties, Inc.*

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B01 Mar-14

## **SHELF LIFE**

Adherent ADP has a shelf life of 18 months from date of manufacture.

## **QUALITY ASSURANCE**

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

---

### **Elementis Specialties**

#### **Asia Head Office China**

**Deuchem (Shanghai) Chemical Co., Ltd.**  
99, Liyang Road,  
Songjiang Industrial Zone,  
Shanghai, China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### **Taiwan**

**Deuchem Co., Ltd.**  
92, Kuang-Fu North Road,  
Hsinchu Industrial Park,  
Hukou, Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### **Malaysia**

**Elementis S.E.A. (Malaysia) Sdn. Bhd.**  
**(1095769-X)**  
62-1, Jalan Tasik Utama 5,  
Medan Niaga Tasik Damai,  
Sungai Besi, 57000 Kuala Lumpur,  
Wilayah Persekutuan, Malaysia  
Tel.: +603-9054 6690  
Fax.: +603-9054 6698

#### **India**

**Elementis Specialties (India) Pvt. Ltd.**  
Unit B, Ground Floor,  
Jaswanti Landmark,  
Mehra Industrial Estate,  
L.B.S Marg, Vikhroli (West),  
Mumbai 400 079, India  
Tel: + 91 22 67421251  
Fax: + 91 22 67421252